

M A T E R I A L S A F E T Y D A T A S H E E T

INTERCOAT CLEAR

Page: 1

PRODUCT NAME: INTERCOAT CLEAR
 PRODUCT CODE: SG-100

HMIS CODES: H F R I
 2 3 0 C

===== SECTION I - MANUFACTURER IDENTIFICATION =====

MANUFACTURER'S NAME: HOUSE OF KOLOR
 ADDRESS : 210 CROSBY ST:
 PICAYUNE, MS 39466

MEDICAL EMERGENCY : 888-345-5732

DATE PRINTED : 11/12/99

TRANSPORTATION EMERGENCY: 888-748-5558

NAME OF PREPARER : Tim Herrington

PRODUCT INFORMATION : 800-328-5139

===== SECTION II - HAZARDOUS INGREDIENTS/SARA III INFORMATION =====

REPORTABLE COMPONENTS	CAS NUMBER	WAPOR PRESSURE	WEIGHT PERCENT
N-butyl acetate (normal butyl acetate) ACGIH TLV/TWA: 150 ppm, 200 ppm STEL OSHA PEL/TWA: 150 ppm, 200 ppm STEL	123-86-4	8.4	68
* Xylene (Xylol) ACGIH TLV: 100 ppm OSHA PEL: 100 ppm	1330-20-7	25	77 20.1
Acrylic resin E ACGIH TLV: None OSHA PEL: None	Proprietary		
* Methyl Isobutyl Ketone (MIBK) ACGIH TLV/TWA: 100 ppm, 150 ppm STEL, OSHA PEL: 100 ppm, 150 ppm STEL	108-10-1	28	68 8.5
Cellulose acetate butyrate ACGIH TLV: Not established OSHA PEL: Not established	009004-36-8	Neglig.	ND
* Ethylbenzene ACGIH TLV/TWA: 100 ppm, 125 ppm STEL OSHA PEL/TWA: 100 ppm, 125 ppm STEL	100-41-4	8.5	68 4.2
* Toluene (Toluol) [65] ACGIH TLV: 50 ppm skin OSHA PEL: 100 ppm; 150 ppm STEL	108-88-3	22	68 0.6

* Indicates toxic chemical(s) subject to the reporting requirements of section 313 of Title III and of 40 CFR 372.

===== SECTION III - PHYSICAL/CHEMICAL CHARACTERISTICS =====

BOILING RANGE: 232 deg F - 284 deg F SPECIFIC GRAVITY (H2O=1): 0.93
 VAPOR DENSITY: Heavier than air EVAPORATION RATE: Slower than ether
 COATING V.O.C.: 5.73 lb/gl MATERIAL V.O.C.: 5.73 lb/gl
 SOLUBILITY IN WATER: Negligible
 APPEARANCE AND ODOR: Opaque or translucent viscous liquid or powder with organic solvent odor.

===== SECTION IV - FIRE AND EXPLOSION HAZARD DATA =====

FLASH POINT: 64 deg F METHOD USED: T.C.C.
 FLAMMABLE LIMITS IN AIR BY VOLUME- LOWER: 1 UPPER: 8
 EXTINGUISHING MEDIA: Foam, alcohol foam, CO2, dry chemical, or water fog.